

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 0 987 773 A2

(12)

## EUROPEAN PATENT APPLICATION

(43) Date of publication:  
22.03.2000 Bulletin 2000/12(51) Int. Cl.<sup>7</sup>: H01L 41/09, H01L 41/047,  
B41J 2/14

(21) Application number: 99117987.0

(22) Date of filing: 17.09.1999


(84) Designated Contracting States:  
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU  
MC NL PT SE  
Designated Extension States:  
AL LT LV MK RO SI(72) Inventor: Kitahara, Tsuyoshi  
Suwa-shi, Nagano (JP)(74) Representative: HOFFMANN - EITLE  
Patent- und Rechtsanwälte  
Arabellastrasse 4  
81925 München (DE)

(30) Priority: 17.09.1998 JP 26319998

(71) Applicant:  
SEIKO EPSON CORPORATION  
Shinjuku-ku, Tokyo (JP)(54) Piezoelectric vibrator unit, manufacturing method thereof, and ink jet recording head  
incorporating the same

(57) In order to simplify a step of forming a conductive layer for external connection and improve the reliability thereof, at least either internal individual electrodes or internal common electrodes, which compose of a piezoelectric vibrator, are connected with each other at through holes situated inner than a end face of the piezoelectric vibrator and connected to either a segment electrode or a common electrode, which are formed on one surface in a longitudinal direction of the piezoelectric vibrator. Accordingly, it is not necessary to form a conductive layer on the end face or a corner portion where such a layer is hardly formed. Furthermore, even if such portions are slightly broken, the conductivity can be maintained.

FIG. 1



Best Available Copy

EP 0 987 773 A2

FP03-0300-
00EP-TD
05.1.31
SEARCH REPORT

## Description

### BACKGROUND OF THE INVENTION

[0001] The present invention relates to a piezoelectric vibrator unit in which internal electrodes are stacked in parallel with the expansion/contraction axis, and more particularly to the structure of internal electrodes, and also to an ink jet recording head.

[0002] As disclosed in Japanese Patent Publication No. 4-1052A, in an ink jet recording head using a piezoelectric vibrator of the longitudinal vibration mode, an elastic plate is placed via a small gap on the back face of a nozzle plate in which plural nozzles are opened, and piezoelectric vibrators having the piezoelectric constant d31, which are obtained by dividing so as to correspond to respective pressure generating chambers of a channel substrate, abuts against the back face of the elastic plate. Ink in a reservoir is guided into the pressure generating chambers via associated ink supply ports, and the ink is then pressurized by the piezoelectric vibrators which are driven by a recording signal, thereby causing the ink to be ejected from the nozzle orifices.

[0003] As disclosed in Japanese Patent Publication No. 7-195688A, for example, such a piezoelectric vibrator is configured in the following manner. It is prepared a single piezoelectric diaphragm in which common electrodes and internal individual electrodes are alternately stacked on each other while sandwiching a piezoelectric material therebetween. In the piezoelectric diaphragm, the internal common electrodes are exposed from a rear end face on the side of the fixed end, and the internal individual electrodes are exposed from a front end face on the side of the free end. The piezoelectric diaphragm is divided such that dummy piezoelectric vibrators are arranged in both sides thereof, and driving piezoelectric vibrators are formed into a comb-like shape in the central portion thereof so that their non-vibrating regions are continuous.

[0004] The internal individual electrodes are connected to a segment electrode which elongates from the front end face to a top face of a non-vibrating region, and the internal common electrodes to a common electrode which elongates from the rear end face to the top face of the non-vibrating region. A driving signal is supplied to the segment electrode and the common electrode via a flexible cable.

[0005] As described above, the external electrodes, which constitute the segment electrode and the common electrode, are formed in an L-like shape on the two faces, i.e., the end faces and the top face. Therefore, there arise problems in that conductive failure easily occurs in a conductive layer in the interface between the end face and the top face, and hence the formation of the conductive layer requires much labor, and that corner edges tend to be broken and a connection failure thereby occurs, thereby lowering the production yield.

### SUMMARY OF THE INVENTION

[0006] The invention has been conducted in view of these problems. It is a first object of the present invention to provide a piezoelectric vibrator unit in which, even when corner edges are slightly broken, the conduction relationship is ensured.

[0007] It is a second object of the present invention to provide a method of manufacturing such a piezoelectric vibrator unit.

[0008] It is a third object of the present invention to provide an ink jet recording head incorporating such a piezoelectric vibrator unit.

[0009] In order to solve the problems, according to the present invention, there are fixed on a fixing substrate a plurality of piezoelectric vibrators in which internal individual electrodes and internal common electrodes are alternately and overlappingly stacked on each other while sandwiching piezoelectric materials therebetween in an area where is to be a vibrating region thereof, comprising: a through hole piercing through the piezoelectric materials in at least one end portions thereof for being filled with a conductive material such that at least either the first conductive layers or the second conductive layers are connected with each other; and an external electrode layer formed on one surface in a longitudinal direction of the piezoelectric vibrators for connecting the conductive material in the through hole.

[0010] The conductive layers on the internal individual electrodes or the internal common electrodes constituting the piezoelectric vibrators are electrically connected with each other and drawn out to a the top face in the longitudinal direction thereof via the through holes arranged inner than the end faces of the piezoelectric vibrators. Therefore, it is not necessary to form conductive layers on the end faces or the corner edge where such a layer is hardly formed.

### BRIEF DESCRIPTION OF THE DRAWINGS

[0011] In the accompanying drawings:

Fig. 1 is a view of one embodiment of the ink jet recording head according to the present invention and showing the section structure in a region of piezoelectric vibrators;

Fig. 2 is an enlarged section view showing the piezoelectric vibrators of the recording head;

Figs. 3A to 3C are views showing steps of the first half of a method of manufacturing the piezoelectric vibrators;

Figs. 4A to 4C are views showing steps of the second half of the method of manufacturing the piezoelectric vibrators;

Fig. 5 is a view showing a method of manufacturing the piezoelectric vibrators according to another embodiment of the present invention;

Fig. 6 is a view showing a state where breakages

are formed in end faces of the piezoelectric vibrators;

Fig. 7 is a section view showing another embodiment of the present invention;

Figs. 8A and 8B are section views showing another embodiment of the present invention; and

Figs. 9A and 9B are section views showing another embodiment of the present invention.

#### DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

[0012] Hereinafter, the present invention will be described in detail on the basis of illustrated embodiments.

[0013] Fig. 1 shows an embodiment of the ink jet recording head according to the present invention. A channel unit 1 is configured by integrally stacking: a nozzle plate 3 in which nozzle orifices 2 are formed at a constant pitch; a channel substrate 7 comprising pressure generating chambers 4 respectively communicating with the associated nozzle orifices 2, and a reservoir 6 for supplying ink to the respective pressure generating chambers 4 via associated ink supply ports 5; and an elastic plate 10 which abuts against front ends of piezoelectric vibrators 9 of the longitudinal vibration mode in a piezoelectric vibrator unit 8, so as to expand and contract the capacity of each of the pressure generating chambers 4.

[0014] The piezoelectric vibrator unit 8 is connected to a flexible cable 11 through which an external driving signal is transmitted, and then housed in and fixed to an unit chamber 13 of a head holder 12, and the channel unit 1 is fixed to an opening face 14 of the head holder 12, thereby constituting the recording head.

[0015] In the piezoelectric vibrator unit 8, the piezoelectric vibrators 9 of the piezoelectric constant d31 are fixed to a fixing substrate 15 so as to coincide with the arrangement pitch of the pressure generating chambers 4, and, as required, dummy piezoelectric vibrators which are slightly wider are fixed to the fixing substrate 15 and at both ends in the arrangement direction of the piezoelectric vibrators 9.

[0016] As shown in Fig. 2, in the piezoelectric vibrators 9, internal common electrodes 17 and internal individual electrodes 18 are alternately stacked on each other while sandwiching a piezoelectric material 19 therebetween. The internal common electrodes 17 are electrically connected to one another in parallel via a conductive layer filling through holes 20 which are opened in an area on the side of the fixed end. The internal individual electrodes 18 are electrically connected to one another in parallel via a conductive layer filling through holes 21 which are opened in an area on the side of the free end. A segment electrode 22 and a common electrode 23 serving also as the internal individual electrodes are formed on the top face of the piezoelectric vibrator 9. The flexible cable 11 is connected

to the electrodes 22 and 23.

[0017] In the embodiment, the through holes 20a and 20b, and 21a and 21b in adjacent two layers are slightly shifted from each other in a direction of the expansion/contraction axis (hereinafter, axial direction), so that the through holes of alternate layers are positioned on one line.

[0018] Fig. 3 shows an embodiment of the method of manufacturing the piezoelectric vibrator unit. A green sheet 32 of a piezoelectric material and having a predetermined thickness is prepared. In the green sheet, through holes 30a and 31a are opened in the vicinity of both ends thereof so as to coincide with the arrangement pitch of the piezoelectric vibrators (Fig. 3A). On the surface of the sheet, a strip-like non-conductive region 33 is formed in a region which is nearer to a center portion than the through holes 31a and which coincides with the front ends of the internal common electrodes 17. Conductive layers 34 and 35 are formed by, for example, printing of a conductive coating material so as to fill the inside of the through holes 30a and 31a (Fig. 3B).

[0019] A green sheet 32' of a piezoelectric material and having a predetermined thickness is stacked on the green sheet 32. In the green sheet 32', through holes 30b and 31b are opened at positions which are slightly different from the through holes 30a and 31a in the axial direction of the piezoelectric vibrators (Fig. 3C). On the surface of the sheet, a strip-like non-conductive region 36 is formed in a region which is nearer to a center portion than the through holes 30b and which coincides with the front ends of the internal individual electrodes 18. Conductive layers 37 and 38 are formed so as to fill the inside of the through holes 30b and 31b (Fig. 4A).

[0020] When the through holes 30a, 30b, 31a, and 31b are formed so that the width in at least one direction is larger than the thickness of the green sheet 32 or 32', the conductive coating material which forms the conductive layers can be surely filled into the through holes 30a, 30b, 31a, and 31b.

[0021] Thereafter, the above-mentioned steps are alternately repeated to stack a required number of layers, so that a green sheet 32" in which through holes 30a and 31a (30b and 31b) are opened in the same manner as described above is stacked, a strip-like non-conductive region 39 is formed in the interface between the segment electrode 22 and the common electrode 23, and conductive layers 40 and 41 are formed so as to fill the insides of the through holes 30a and 31a (30b and 31b) (Fig. 4B).

[0022] The green sheets of the piezoelectric material are dried and then baked so as to constitute a single piezoelectric material diaphragm 42. Slits 44 are formed at a pitch which coincides with the arrangement pitch of the through holes 31a (31b) on the side of the front end serving as the free end, by oblique cutting lines C (see Fig. 1). The cutting lines are formed by a cutting tool 43 such as a wire saw or a dicing saw which is advanced to

an area where at least the conductive layer 40 can be split into mutually separated portions, in such a manner that each slit is formed as a slope a top end of which is situated in the rear end side and a bottom end of which is situated in the front end side. As a result, the diaphragm is cut into a comb-like shape so that the rear end side is a continuous portion (Fig. 4C).

[0023] In the embodiment, the slits are formed in the piezoelectric material diaphragm 42. Alternatively, as shown in Fig. 5, the slits 44 may be formed after the non-vibrating regions are fixed to a fixing substrate 45 by means of an adhesive agent or the like. In the alternative, the working efficiency can be improved.

[0024] In the thus configured ink jet recording head, when a driving signal is supplied through the flexible cable 11, the driving signal is applied to the internal individual electrodes 18 via the segment electrode 22 and the through holes 21a and 21b of each layer, and to the internal common electrodes 17 via the common electrode 23 and the through holes 20a and 20b of each layer, with the result that the layers of the piezoelectric material 19 contract in the axial direction.

[0025] The capacity of the corresponding one of the pressure generating chambers 4 is thus expanded. Therefore, the ink in the reservoir 6 flows into the pressure generating chamber 4 via the ink supply port 5. When the supply of the driving signal is stopped after elapse of a predetermined time period, the piezoelectric vibrator 9 returns to its original state to relatively contract the capacity of the pressure generating chamber 4, whereby an ink droplet is ejected from the nozzle orifice 2.

[0026] No external electrode for connection exists on the front end face 9a and the rear end face 9b of each of the piezoelectric vibrators 9. Even when minute breakages 9c and 9d which are not so large and hence does not reach the through holes 20 and 21 exist as shown in Fig. 6, therefore, the conduction relationships among the segment electrode 22 or the common electrode 23 and the internal individual electrodes 18 or the internal common electrodes 17 can be maintained. According to this configuration, even when breakages are formed during a process of splitting the single piezoelectric material diaphragm 42 by forming slits into the individual piezoelectric vibrators 9, or that of mounting the unit into a recording head, there arises no substantial disadvantage and the production yield can be improved.

[0027] In the above embodiment, the internal common electrodes 17, the internal individual electrodes 18, the segment electrode 22, and the common electrode 23 are formed so that their ends are exposed to the outside from the both end faces of the piezoelectric vibrator 9. Alternatively, as shown in Fig. 7, these electrodes may be formed so that their ends are positioned between the through holes 20 or 21 and the front end face 9a or the rear end face 9b. In the alternative, even when a conductive material abuts against the end faces 9a and 9b, the internal common electrodes 17 and the internal indi-

vidual electrodes 18 are prevented from being short-circuited.

[0028] In the above embodiment, the connection among the internal common electrodes 17, and that among the internal individual electrodes 18 are attained by means of the through holes 20 and 21, respectively. Alternatively, as shown in Figs. 8A and 8B, an external electrode 24 or 25 may be formed on one of the front end face and the rear end face, and the internal common electrodes 17 or the internal individual electrodes 18 may be connected to one another in parallel via the external electrode 24 or 25, and then connected to the common electrode 23 or the segment electrode 22. Also in the alternative, the production yield can be improved.

[0029] In the above embodiment, the through holes 20a and 20b, or 21a and 21b in the layers are slightly shifted with each other in the axial direction. Alternatively, as shown in Fig. 9A, the through holes may be formed on the same axial line A or B, or, as shown in Fig. 9B, the through holes on the side of the fixed end may be formed as a through slit 26. Also in the alternatives, the same effects can be attained.

[0030] As described above, according to the present invention, there are fixed on a fixing substrate a plurality of piezoelectric vibrators in which internal individual electrodes and internal common electrodes are alternately and overlappingly stacked on each other while sandwiching piezoelectric materials therebetween in an area where is to be a vibrating region thereof, comprising: a through hole piercing through the piezoelectric materials in at least one end portions thereof for being filled with a conductive material such that at least either the first conductive layers or the second conductive layers are connected with each other; and an external electrode layer formed on one surface in a longitudinal direction of the piezoelectric vibrators for connecting the conductive material in the through hole. Accordingly, the internal individual electrodes constituting the piezoelectric vibrators, or the internal common electrodes can be connected to one another via the through holes which are positioned inside the end face of the piezoelectric vibrators, so as to be drawn to the surface of the longitudinal direction. Therefore, formation of a conductive layer is not required on an end face or an edge where such a layer is hardly formed. As a result, the reliability can be enhanced.

[0031] Furthermore, no external electrode exists on an end face of each piezoelectric vibrator in which breakages are formed in a relatively easy manner. Even when breakages are formed during a step of splitting the piezoelectric vibrators into a comb-like shape or mounting the vibrator unit into a recording head, therefore, there arises no substantial disadvantage and the production yield can be improved.

[0032] Although the present invention has been shown and described with reference to specific preferred embodiments, various changes and modifications will be apparent to those skilled in the art from the

teachings herein. Such changes and modifications as are obvious are deemed to come within the spirit, scope and contemplation of the invention as defined in the appended claims.

#### Claims

1. A piezoelectric vibrator unit in which first conductive layers to be internal individual electrodes and second conductive layers to be internal common electrodes are alternately and overlappingly stacked on each other while sandwiching piezoelectric materials therebetween, comprising:
  - a through hole piercing through the piezoelectric materials in at least one end portions thereof for being filled with a conductive material such that at least either the first conductive layers or the second conductive layers are connected with each other; and
  - an external electrode layer for connecting the conductive material in the through hole.
2. The piezoelectric vibrator unit as set forth in claim 1, wherein the unit includes a plurality of piezoelectric vibrators and the through hole for connecting the first conductive layers is formed in every piezoelectric vibrator.
3. The piezoelectric vibrator unit as set forth in claim 1, wherein the conductive layers on which the through holes are formed are electrically connected by the conductive material filling the through hole.
4. The piezoelectric vibrator unit as set forth in claim 1, wherein the through holes of the respective layers is situated on the same line.
5. The piezoelectric vibrator unit as set forth in claim 1, wherein the through holes alternate ones of the respective layers are situated on the same line.
6. The piezoelectric vibrator unit as set forth in claim 1, end faces of the respective conductive layers are situated nearer to a center portion than end faces of the piezoelectric vibrator.
7. The piezoelectric vibrator unit as set forth in claim 1, wherein the width of the through hole is larger than the thickness of the piezoelectric material of each layer.
8. The piezoelectric vibrator unit as set forth in claim 1, wherein the respective piezoelectric vibrators are divided into a comb-like shape by slits such that non-vibrating regions of the respective piezoelectric vibrators are connected with each other.
9. The piezoelectric vibrator unit as set forth in claim 1, the external electrode layer is made of a material identical with a material of the internal electrodes.
10. The piezoelectric vibrator unit as set forth in claim 1, wherein one face extending in a longitudinal direction of the each piezoelectric vibrator is fixed to a fixing base.
11. The piezoelectric vibrator unit as set forth in claim 1, wherein the piezoelectric vibrator is of longitudinal vibration type which expands and contracts in a direction perpendicular to the stacking direction of the conductive layers and the piezoelectric materials.
12. The piezoelectric vibrator unit as set forth in claim 1, wherein a segment electrode and a common electrode is provided as the external electrode layer.
13. The piezoelectric vibrator unit as set forth in claim 1, wherein an external electrode connected to the external electrode layer is provided on an end portion of the piezoelectric vibrator a side of which the through hole is absent.
14. A method of manufacturing a piezoelectric vibrator unit, comprising the steps of:
  - (a) preparing a green sheet in which through holes are opened in the vicinity of at least one end portion thereof which is to be a vibrating region of the piezoelectric vibrator;
  - (b) forming a conductive material layer on the green sheet while filling the through holes such that a strip-like non-conductive region is formed in an area where is nearer to a center portion thereof than the through holes and is to be coincident with a distal end of an internal common electrode;
  - (c) repeating the steps (a) and (b) to stack required number of layers until through holes to be electrically connected with a segment electrode are filled;
  - (d) baking the above to form a single piezoelectric material diaphragm; and
  - (e) forming slits on the piezoelectric material diaphragm so as to elongate to an area where at least the conductive layers can be separated from each other to constitute piezoelectric vibrators.
15. A method of manufacturing a piezoelectric vibrator unit, comprising the steps of:
  - (a) preparing a green sheet in which through holes are opened in the vicinity of at least one

end portion thereof which is to be a vibrating region of the piezoelectric vibrator;

(b) forming a conductive material layer on the green sheet while filling the through holes such that a strip-like non-conductive region is formed in an area where is nearer to a center portion thereof than the through holes and is to be coincident with a distal end of an internal common electrode;

(c) preparing a next green sheet in which through holes are opened in the vicinity of at least one end portion thereof which is to be the vibrating region of the piezoelectric vibrator;

(d) forming a conductive material layer on the green sheet while filling the through holes such that a strip-like non-conductive region where is to be coincident with a distal end of an internal individual electrode;

(e) repeating the steps (a) to (d) to stack required number of layers until through holes to be electrically connect with a segment electrode is filled;

(f) baking the above to form a single piezoelectric material diaphragm; and

(g) forming slits on the piezoelectric material diaphragm so as to elongate to an area where at least the conductive layers can be separated from each other to constitute piezoelectric vibrators.

16. The piezoelectric vibrator unit as set forth in claim 14, wherein the through holes are opened so as to coincide with an arrangement pitch of the piezoelectric vibrators.

17. The piezoelectric vibrator unit as set forth in claim 15, wherein the through holes are opened so as to coincide with an arrangement pitch of the piezoelectric vibrators.

18. The piezoelectric vibrator unit as set forth in claim 14, wherein the slits are formed so as to coincide with an arrangement pitch of through holes formed in one end portion which is to be a free end of the piezoelectric vibrator.

19. The piezoelectric vibrator unit as set forth in claim 15, wherein the slits are formed so as to coincide with an arrangement pitch of through holes formed in one end portion which is to be a free end of the piezoelectric vibrator.

20. An ink jet recording head comprising:


a piezoelectric vibrator unit in which first conductive layers to be internal individual electrodes and second conductive layers to be internal common electrodes are alternately and

overlappingly stacked on each other while sandwiching a piezoelectric material therebetween, including:


a through hole piercing through the piezoelectric materials in at least one of end portions of thereof for being filled with conductive material such that at least one of the first conductive layers with each other and the second conductive layers with each other are connected; and an external electrode layer for connecting the conductive material in the through hole;

a channel unit including a pressure generating chamber pressurized by the piezoelectric vibrator unit, which communicates with both of a reservoir and a nozzle orifice; and a head holder for holding the piezoelectric vibrator unit and the channel unit.


**FIG. 1**




**FIG. 2**



**FIG. 3A**



**FIG. 3B**



**FIG. 3C**






FIG. 4A




FIG. 4B





FIG. 4C



*FIG. 5*




FIG. 6







FIG. 7




**FIG. 8A**




**FIG. 8B**



**FIG. 9A**



**FIG. 9B**



(12) **EUROPEAN PATENT APPLICATION**

(88) Date of publication A3:  
07.07.2004 Bulletin 2004/28

(51) Int Cl.7: **H01L 41/083**, H01L 41/047,  
B41J 2/14

**(43) Date of publication A2:**  
**22.03.2000 Bulletin 2000/12**

(21) Application number: 99117987.0

**(22) Date of filing: 17.09.1999**

**(84) Designated Contracting States:**  
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU**  
**MC NL PT SE**  
**Designated Extension States:**  
**AL LT LV MK RO SI**

**(72) Inventor: Kitahara, Tsuyoshi**  
**Suwa-shi, Nagano (JP)**

**(74) Representative: HOFFMANN - EITL**  
**Patent- und Rechtsanwälte**  
**Arabellastrasse 4**  
**81925 München (DE)**

**(30) Priority: 17.09.1998 JP 26319998**


(71) Applicant: SEIKO EPSON CORPORATION  
Shinjuku-ku, Tokyo (JP)

(54) **Piezoelectric vibrator unit, manufacturing method thereof, and ink jet recording head incorporating the same**

(57) In order to simplify a step of forming a conductive layer for external connection and improve the reliability thereof, at least either internal individual electrodes or internal common electrodes, which compose of a piezoelectric vibrator, are connected with each other at through holes situated inner than a end face of the piezoelectric vibrator and connected to either a segment

electrode or a common electrode, which are formed on one surface in a longitudinal direction of the piezoelectric vibrator. Accordingly, it is not necessary to form a conductive layer on the end face or a corner portion where such a layer is hardly formed. Furthermore, even if such portions are slightly broken, the conductivity can be maintained.

FIG. 1





European Patent  
Office

# EUROPEAN SEARCH REPORT

Application Number  
EP 99 11 7987

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	US 4 523 121 A (HAMATSUKI TAKESHIGE ET AL) 11 June 1985 (1985-06-11) * column 1, line 7-66 *	1,3,4,7, 11	H01L41/083 H01L41/047 B41J2/14
Y	* column 4, line 58-68 * * column 8, line 31 - column 9, line 52 * * figures 14,15 *	9	
X	--- PATENT ABSTRACTS OF JAPAN vol. 1997, no. 10, 31 October 1997 (1997-10-31) -& JP 09 162450 A (MATSUSHITA ELECTRIC IND CO LTD), 20 June 1997 (1997-06-20) * abstract; figures 1,2 *	1,3,4,6	
Y	--- EP 0 860 279 A (SEIKO EPSON CORP) 26 August 1998 (1998-08-26) * the whole document *	2,8-12, 20	
Y	--- EP 0 860 279 A (SEIKO EPSON CORP) 26 August 1998 (1998-08-26) * the whole document *	2,8-12, 20	TECHNICAL FIELDS SEARCHED (Int.Cl.7)  H01L B41J
X	--- PATENT ABSTRACTS OF JAPAN vol. 1997, no. 03, 31 March 1997 (1997-03-31) -& JP 08 316542 A (NIPPON CEMENT CO LTD), 29 November 1996 (1996-11-29) * abstract; figures 2,3 *	1,3-5	
A	--- WO 98/02927 A (NIHON CEMENT KABUSHIKI KAISHA ;YAMAKAWA TAKAHIRO (JP); EZAKI TORU) 22 January 1998 (1998-01-22) * page 22, line 23 - page 26, line 19; figures 12,13A-13D *	1,3,4,6	
The present search report has been drawn up for all claims			
Place of search <b>MUNICH</b>		Date of completion of the search <b>18 May 2004</b>	Examiner <b>Meul, H</b>
<p><b>CATEGORY OF CITED DOCUMENTS</b></p> <p>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document</p> <p>T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &amp;: member of the same patent family, corresponding document</p>			

EPO FORM 1503 03.02 (P04C01)

**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 11 7987

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

18-05-2004

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 4523121	A	11-06-1985	JP 1472361 C	27-12-1988
			JP 58196068 A	15-11-1983
			JP 63017354 B	13-04-1988
			JP 1857861 C	27-07-1994
			JP 58196069 A	15-11-1983
			JP 63034636 B	11-07-1988
			JP 58196070 A	15-11-1983
			JP 58196071 A	15-11-1983
			JP 58196072 A	15-11-1983
			JP 58196073 A	15-11-1983
			JP 58196074 A	15-11-1983
			JP 1871855 C	06-09-1994
			JP 4051992 B	20-08-1992
			JP 58196075 A	15-11-1983
			JP 1944761 C	23-06-1995
			JP 6071102 B	07-09-1994
			JP 58196076 A	15-11-1983
			JP 1882024 C	10-11-1994
			JP 6005794 B	19-01-1994
			JP 58196077 A	15-11-1983
			JP 58196078 A	15-11-1983
			JP 1728730 C	29-01-1993
			JP 4009390 B	20-02-1992
			JP 58196079 A	15-11-1983
			AU 553391 B2	10-07-1986
			AU 1442283 A	17-11-1983
			CA 1206193 A1	17-06-1986
			DE 3378393 D1	08-12-1988
			EP 0094078 A2	16-11-1983
			BR 8302536 A	17-01-1984
			KR 8600255 B1	21-03-1986
-----				
JP 09162450	A	20-06-1997	NONE	
-----				
EP 0860279	A	26-08-1998	DE 69805457 D1	27-06-2002
			DE 69805457 T2	16-01-2003
			EP 0860279 A1	26-08-1998
			JP 3381775 B2	04-03-2003
			JP 10291314 A	04-11-1998
			US 6241346 B1	05-06-2001
-----				
JP 08316542	A	29-11-1996	NONE	
-----				
WO 9802927	A	22-01-1998	JP 3411757 B2	03-06-2003
			JP 10051044 A	20-02-1998
			JP 10084143 A	31-03-1998

EPO FORM P0459

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82



**ANNEX TO THE EUROPEAN SEARCH REPORT  
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 11 7987

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.  
The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

18-05-2004

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9802927      A	AT	248438 T	15-09-2003
	CN	1230292 A	29-09-1999
	DE	69724437 D1	02-10-2003
	EP	0914681 A1	12-05-1999
	HK	1031272 A1	12-12-2003
	WO	9802927 A1	22-01-1998
	KR	2000023735 A	25-04-2000
	TW	432730 B	01-05-2001
	US	6172447 B1	09-01-2001
-----			

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**